

FORM PTO-1399 (Modified)
(REV 11/2000)

U.S. DEPARTMENT OF COMMERCE PATENT AND TRADEMARK OFFICE

ATTORNEY'S DOCKET NUMBER

TRANSMITTAL LETTER TO THE UNITED STATES

27428/37457

DESIGNATED/ELECTED OFFICE (DO/EO/US)

U.S. APPLICATION NO. (IF KNOWN, SEE 37 CFR

CONCERNING A FILING UNDER 35 U.S.C. 371

09/857831

INTERNATIONAL APPLICATION NO.

INTERNATIONAL FILING DATE

PRIORITY DATE CLAIMED

PCT/EP99/08003

21 October 1999

10 December 1998

TITLE OF INVENTION

COATING OF OBJECTS

APPLICANT(S) FOR DO/EO/US

Kai K.O. Bar, Rainer Gaus, Martin Sedlmeyr, and Stefan Schiele

Applicant herewith submits to the United States Designated/Elected Office (DO/EO/US) the following items and other information:


1. ☒ This is a **FIRST** submission of items concerning a filing under 35 U.S.C. 371.
2. ☐ This is a **SECOND** or **SUBSEQUENT** submission of items concerning a filing under 35 U.S.C. 371.
3. ☐ This is an express request to begin national examination procedures (35 U.S.C. 371(f)). The submission must include items (5), (6), (9) and (24) indicated below.
4. ☐ The US has been elected by the expiration of 19 months from the priority date (Article 31).
5. ☒ A copy of the International Application as filed (35 U.S.C. 371 (c) (2))
 - a. ☐ is attached hereto (required only if not communicated by the International Bureau).
 - b. ☒ has been communicated by the International Bureau.
 - c. ☐ is not required, as the application was filed in the United States Receiving Office (RO/US).
6. ☒ An English language translation of the International Application as filed (35 U.S.C. 371(c)(2)).
 - a. ☒ is attached hereto.
 - b. ☐ has been previously submitted under 35 U.S.C. 154(d)(4).
7. ☒ Amendments to the claims of the International Application under PCT Article 19 (35 U.S.C. 371 (c)(3))
 - a. ☐ are attached hereto (required only if not communicated by the International Bureau).
 - b. ☐ have been communicated by the International Bureau.
 - c. ☐ have not been made; however, the time limit for making such amendments has NOT expired.
 - d. ☒ have not been made and will not be made.
8. ☐ An English language translation of the amendments to the claims under PCT Article 19 (35 U.S.C. 371(c)(3)).
9. ☐ An oath or declaration of the inventor(s) (35 U.S.C. 371 (c)(4)).
10. ☐ An English language translation of the annexes of the International Preliminary Examination Report under PCT Article 36 (35 U.S.C. 371 (c)(5)).
11. ☐ A copy of the International Preliminary Examination Report (PCT/PEA/409).
12. ☐ A copy of the International Search Report (PCT/ISA/210).

Items 13 to 20 below concern document(s) or information included:

13. ☐ An Information Disclosure Statement under 37 CFR 1.97 and 1.98.
14. ☐ An assignment document for recording. A separate cover sheet in compliance with 37 CFR 3.28 and 3.31 is included.
15. ☒ A **FIRST** preliminary amendment.
16. ☐ A **SECOND** or **SUBSEQUENT** preliminary amendment.
17. ☐ A substitute specification.
18. ☐ A change of power of attorney and/or address letter.
19. ☐ A computer-readable form of the sequence listing in accordance with PCT Rule 13ter.2 and 35 U.S.C. 1.821 - 1.825.
20. ☐ A second copy of the published international application under 35 U.S.C. 154(d)(4).
21. ☐ A second copy of the English language translation of the international application under 35 U.S.C. 154(d)(4).
22. ☒ Certificate of Mailing by Express Mail
23. ☐ Other items or information:

531 Rec'd PCT

07 JUN 2001

U.S. APPLICATION NO. (IF KNOWN, SEE 37 CFR 1.492 (a) (1) - (5)) : 69785783		INTERNATIONAL APPLICATION NO. PCT/EP99/08003		ATTORNEY'S DOCKET NUMBER 27428/37457	
24. The following fees are submitted: BASIC NATIONAL FEE (37 CFR 1.492 (a) (1) - (5)) :				CALCULATIONS PTO USE ONLY	
<input type="checkbox"/> Neither international preliminary examination fee (37 CFR 1.482) nor international search fee (37 CFR 1.445(a)(2)) paid to USPTO and International Search Report not prepared by the EPO or JPO				\$1000.00	
<input checked="" type="checkbox"/> International preliminary examination fee (37 CFR 1.482) not paid to USPTO but International Search Report prepared by the EPO or JPO				\$860.00	
<input type="checkbox"/> International preliminary examination fee (37 CFR 1.482) not paid to USPTO but international search fee (37 CFR 1.445(a)(2)) paid to USPTO				\$710.00	
<input type="checkbox"/> International preliminary examination fee (37 CFR 1.482) paid to USPTO but all claims did not satisfy provisions of PCT Article 33(1)-(4)				\$690.00	
<input type="checkbox"/> International preliminary examination fee (37 CFR 1.482) paid to USPTO and all claims satisfied provisions of PCT Article 33(1)-(4)				\$100.00	
ENTER APPROPRIATE BASIC FEE AMOUNT =				\$860.00	
Surcharge of \$130.00 for furnishing the oath or declaration later than _____ months from the earliest claimed priority date (37 CFR 1.492 (e)). <input type="checkbox"/> 20 <input type="checkbox"/> 30				\$0.00	
CLAIMS	NUMBER FILED	NUMBER EXTRA	RATE		
Total claims	14 - 20 =	0	x \$18.00	\$0.00	
Independent claims	3 - 3 =	0	x \$80.00	\$0.00	
Multiple Dependent Claims (check if applicable) <input type="checkbox"/>				\$0.00	
TOTAL OF ABOVE CALCULATIONS =				\$860.00	
<input type="checkbox"/> Applicant claims small entity status. (See 37 CFR 1.27). The fees indicated above are reduced by 1/2.				\$0.00	
SUBTOTAL =				\$860.00	
Processing fee of \$130.00 for furnishing the English translation later than _____ months from the earliest claimed priority date (37 CFR 1.492 (f)). <input type="checkbox"/> 20 <input type="checkbox"/> 30				\$0.00	
TOTAL NATIONAL FEE =				\$860.00	
Fee for recording the enclosed assignment (37 CFR 1.21(h)). The assignment must be accompanied by an appropriate cover sheet (37 CFR 3.28, 3.31) (check if applicable). <input type="checkbox"/>				\$0.00	
TOTAL FEES ENCLOSED =				\$860.00	
				Amount to be: refunded	\$
				charged	\$
a. <input checked="" type="checkbox"/> A check in the amount of \$860.00 to cover the above fees is enclosed. b. <input type="checkbox"/> Please charge my Deposit Account No. _____ in the amount of _____ to cover the above fees. A duplicate copy of this sheet is enclosed. c. <input checked="" type="checkbox"/> The Commissioner is hereby authorized to charge any additional fees which may be required, or credit any overpayment to Deposit Account No. 13-2855 . A duplicate copy of this sheet is enclosed. d. <input type="checkbox"/> Fees are to be charged to a credit card. WARNING: Information on this form may become public. Credit card information should not be included on this form. Provide credit card information and authorization on PTO-2038.					
NOTE: Where an appropriate time limit under 37 CFR 1.494 or 1.495 has not been met, a petition to revive (37 CFR 1.137(a) or (b)) must be filed and granted to restore the application to pending status.					
SEND ALL CORRESPONDENCE TO: <div style="display: flex; justify-content: space-between;"> <div style="width: 45%;"> Nate F. Scarpelli MARSHALL, O'TOOLE, GERSTEIN, MURRAY & BORUN 233 South Wacker Drive 6300 Sears Tower Chicago, Illinois 60606-6402 Tel.: (312) 474-6300 Fax: (312) 474-0448 </div> <div style="width: 45%; text-align: center;">  SIGNATURE Nate F. Scarpelli NAME 22,320 REGISTRATION NUMBER June 7, 2001 DATE </div> </div>					

09/857831

531 Rec'd PCT

07 JUN 2001

New Patent Application for:

KAI K.O. BÄR, ET AL.

For:

COATING OF OBJECTS

Mailing Certificate for:

Transmittal Letter To The United
States Designated/Elected Office
(DO/EO/US) Concerning A Filing
Under 35 U.S.C. 371

Attorney Docket No.:


27428/37457

"EXPRESS MAIL" mailing label No. EL 827655984 US

Date of Deposit:

June 7, 2001

I hereby certify that this paper (or fee) is being deposited
with the United States Postal Service "EXPRESS MAIL POST
OFFICE TO ADDRESSEE" service under 37 CFR \$1.10 on the date
indicated above and is addressed to the Commissioner for
Patents, Box PCT, Washington, D.C., 20231.



Richard Zimmermann

--6. (Amended) Method according to Claim 1, characterized in that the drying is completed within 5 seconds, in particular within 3 seconds, after the application of the impregnation or coating agent.--

--7. (Amended) Method according to Claim 1, characterized in that the object (1; 5) being processed is conveyed continually in a longitudinal direction, in the course of which it first passes through an application zone in which the coating and/or impregnation agent (22) is applied, and that the object (1; 5) or more specifically its coated or impregnated longitudinal sections are conveyed into a drying zone in which the coated or impregnated surface is irradiated with the infrared radiation.--

--10. (Amended) Method according to Claim 1, including providing an infrared lamp (11) to dry an object (1; 5) coated or impregnated with a coating agent and/or impregnation agent (22), in particular to dry lacquered wood.--

--11. (Amended) Method according to Claim 10, wherein the infrared lamp (11) is a halogen lamp.--

--12. (Amended) Method according to Claim 10,
wherein the infrared lamp (11) is constructed as a tubular
radiator with an incandescent filament (12) that extends
linearly within a tube (13) that is transparent to radiation,
in particular within a quartz-glass tube.--

--13. (Amended) Method according to Claim 12,
wherein the infrared lamp (11) is combined with a reflector
element (10) that extends along the tube (13) and in cross
section has a groove-like structure, enclosing back side of
the tube in such a way that the infrared radiation is
intensified by addition of reflected radiation to the
radiation emitted towards the front side.--

REMARKS

Respectfully submitted,


Nate F. Scarpelli, Reg. #22,320
MARSHALL, O'TOOLE, GERSTEIN,
MURRAY & BORUN
6300 Sears Tower
233 S. Wacker Drive
Chicago, Illinois 60606
Tel.: (312) 474-6300
Fax: (312) 474-0448

Dated: June 7, 2001

07 JUN 2001

VERSION WITH MARKINGS TO SHOW CHANGES MADE

Please amend claims 3, 6, 7, and 10-13 as follows:

--3. (Amended) Method according to Claim 1 [or 2], characterized in that the infrared radiation comprises substantial components, which bring about the drying, in the near infrared, in particular at wavelengths below 1.0 μm --

--6. (Amended) Method according to Claim 1 [one of the claims 1-5], characterized in that the drying is completed within 5 seconds, in particular within 3 seconds, after the application of the impregnation or coating agent.--

--7. (Amended) Method according to Claim 1 [one of the claims 1-6], characterized in that the object (1; 5) being processed is conveyed continually in a longitudinal direction, in the course of which it first passes through an application zone in which the coating and/or impregnation agent (22) is applied, and that the object (1; 5) or more specifically its coated or impregnated longitudinal sections are conveyed into a drying zone in which the coated or impregnated surface is irradiated with the infrared radiation.--

--10. (Amended) [Employment of] Method according to Claim 1, including providing an infrared lamp (11) to dry an object (1; 5) coated or impregnated with a coating agent and/or impregnation agent (22), in particular to dry lacquered

wood[, in cases such that the nature of the coating agent and/or impregnation agent (22) is as described in Claim 1 and/or in Claim 2].--

--11. (Amended) [Employment] Method according to Claim 10, wherein the infrared lamp (11) is a halogen lamp.--

--12. (Amended) [Employment] Method according to Claim 10 [or 11], wherein the infrared lamp (11) is constructed as a tubular radiator with an incandescent filament (12) that extends linearly within a tube (13) that is transparent to radiation, in particular within a quartz-glass tube.--

--13. (Amended) [Employment] Method according to Claim 12, wherein the infrared lamp (11) is combined with a reflector element (10) that extends along the tube (13) and in cross section has a groove-like structure, enclosing back side of the tube in such a way that the infrared radiation is intensified by addition of reflected radiation to the radiation emitted towards the front side.--

-1-

COATING OF OBJECTSDescription

The invention relates to a method of drying coated and/or impregnated objects, in particular lacquered wood, in cases such that a coating and/or impregnation agent that has been applied to the object concerned contains a solvent or dilution fluid, in particular water, that is to be driven out during the drying, and such that the solvent or diluting fluid has the property of penetrating into the object while in the undried state, so that uniformly structured regions, in particular fibres of the object, change their position in the object and after a characteristic period of time following application of the impregnation or coating agent change the surface structure in such a way that subsequent treatment of the surface (polishing, coating or impregnating) is necessary or desirable. The invention further relates to a method of drying a coated and/or impregnated object, in particular lacquered wood, in cases such that a coating and/or impregnation agent that has been applied to the object concerned comprises a component, in particular colouring pigments, having the property that because of its presence in the region of the

surface and/or in the coating the quality of the coating or impregnation is insured, but also having the property that in the undried state it penetrates into the object and after a characteristic period of time following application of the impregnation or coating agent it is no longer present in sufficient quantity in the region of the surface and/or in the coating, so that a subsequent treatment of the surface, in particular a secondary lacquering, is necessary or desirable. Finally the invention relates to the employment of a means of drying coated and/or impregnated objects.

When water-based lacquers are used, the problem arises that in the region of an initially smooth wooden surface the penetration of water causes certain regions or fibres in the wood, which in themselves are uniformly structured, to rise up because the entering water makes the uniformly structured regions swell and/or forces them apart. After drying of the lacquer, or of the lacquer and the wooden object, it is therefore customary to polish the lacquered surface and apply another lacquer coating. In this case the coating first applied functions as a water barrier, because it prevents water from penetrating into the wood.

The same or at least similar effects appear in other absorbent materials that comprise a plurality of regions and/or fibres that are in themselves uniformly structured. The effects are also produced not only by water-based lacquers but in general by coating agents and/or impregnation agents that are water-based or can be diluted by water, for instance scumbles, mordants, flame-retardant coatings and/or other protective and impregnation agents that are applied to the surface of the object to be treated. Furthermore, the effects are produced not only by coating and/or impregnation agents that contain water, but also by agents containing other solvents and/or dilution fluids that are to be driven out and/or bound during drying.

When pigmented lacquers are used and the objects to be coated are made of wood or similarly absorbent materials, it can also happen that after a characteristic period of time the pigments appear to fade, because they have migrated into the interior of the object. In order to produce the intended visual effect, the pigments should remain near the surface of the object and/or within the applied layer, but in this case they penetrate the object and the desired effect is lost. That is, the coating and/or impregnation is not of the required or desired quality. In this

situation, again, further treatment is necessary or at least desirable, in particular a secondary lacquering.

Not only pigments but also other components of coating and/or impregnation agents, which are crucial for the quality of the coating or impregnation, can become less effective as a result of inward migration when applied to the surface of an object that absorbs or allows penetration of such materials.

Drying of the coated and/or impregnated objects can be brought about passively by waiting until the moist component has become distributed through the surroundings of the object, and/or over the object and into its surroundings, as a result of a concentration gradient. Especially in industrial production lines, however, drying is actively induced by passing the objects to be dried through an oven, for example, or irradiating them with infrared radiation. Another known procedure is to use UV radiation in order to harden, in particular, water-based coating and/or impregnation agents. Here the solvent, in this case water, is permanently bound to the coating and/or impregnation agent by the hardening process. The term "drying" is understood to include this binding of the moist components so that they can no longer become separated from the agent.

Water is known to be a preferred solvent and/or dilution fluid, because it is environmentally compatible. In particular, for the drying process open systems can be used that discharge the expelled water into the surroundings, in some circumstances after it has passed through a filter.

An objective of the present invention is to disclose a method of the kind cited at the outset, for drying coated and/or impregnated objects, the use of which eliminates the need for subsequent treatment of the coated and/or impregnated surface. Another objective of the invention is to disclose how a means of drying coated and/or impregnated objects can be employed in such a way as to make it unnecessary for such objects to be given secondary treatment after they have been dried.

The first objective is achieved by a method with the characteristics given in Claim 1 and/or by a method with the characteristics given in Claim 2. The employment of means is the subject matter of Claim 10. Further developments are specified by the subordinate claims in each case.

Regarding the method, drying is completed before the characteristic time period has elapsed, at the end of which the position of the fibres, or more

generally the individually uniformly structured regions, would have changed so greatly that a subsequent treatment of the surface would be necessary or desirable, or at the end of which the component crucial for the quality of the coating or impregnation would have migrated into the substrate to a sufficient extent that a subsequent treatment of the surface would be necessary or desirable.

Preferably the infrared radiation used for this purpose comprises substantial components, which bring about the drying, in the near infrared and in particular is at wavelengths below 1.0 m. The term "near infrared" is understood to mean the wavelength range between the visible region and 1.4 m. It is advantageous that only a small amount of energy is contributed to the near infrared by thermal radiation from objects at room temperature. Electromagnetic radiation in the near infrared can thus easily be distinguished from the thermal radiation of nearby objects at room temperature, which are unavoidably present in most situations. Therefore near-infrared radiation can be especially well controlled.

Furthermore, water has an especially high absorptance for near-infrared radiation, so that water molecules can be specifically excited and expelled from

the not yet dried coating or impregnation agent. This has the advantage that the remaining structure - other components of the coating or impregnation agent and in particular the object to the surface of which these have been applied - is heated negligibly or not at all. A subsequent cooling or waiting time can thus be eliminated. Further processing or storage, which for example can involve stacking the objects, can be done immediately after the drying process, with no interruption.

In a further development the infrared radiation is adjusted and/or filtered before it is incident on the surface, in such a way as to exclude spectral components of the radiation that would cause an undesired heating of the coating or impregnation agent and/or of the object. For this filtering optical filters known from the state of the art or familiar to the expert can be used, in particular transparent filters. Such means can also be used to achieve a targeted excitation of solvents or dilution fluids other than water.

In a further development the infrared radiation has a spectral peak of radiation flux density in the near infrared, in particular at wavelengths below 1.0 μ m. Preferably the infrared radiation is

emitted as thermal radiation from a radiation emitter heated to temperatures of 2500 K or higher, in particular 2900 K or higher. This procedure has several advantages. Firstly, because of the large difference in temperature between the radiation emitter and the surroundings, which are ordinarily at or approximately at room temperature, the radiation emitter cools down rapidly when the heating is turned off. In addition the emitted radiation density, i.e. the radiant energy sent out from the surface of the emitter, is larger at high temperatures than at lower temperatures. Hence the volume of the radiation emitter can be made correspondingly small, so that its overall heat capacity is low. The resulting radiation emitter can be excellently well controlled at the high temperatures mentioned above. Preferably the heating is achieved electrically in the known manner, by causing an electrical current to flow through a radiation emitter constructed as an electric resistor. Electric currents can be inexpensively controlled by known means.

In particular in the case of wood coated with water-based lacquer, it has been found that wood fibres typically begin to rise up after 5 seconds. If the water-based lacquer contains pigments, a fading of the pigment by migration sufficient to have a negative

influence on the quality of the lacquer is typically observable after 3 seconds. It is therefore preferable for the drying to be completed within 5 seconds, in particular within 3 seconds after the impregnation or coating agent has been applied.

In the case of industrial coating or impregnation of objects, the latter are customarily conveyed continuously in a particular transport direction. In accordance with the invention the object concerned preferably passes through an application zone, in which the coating and/or impregnation agent is applied, and then is conveyed further such that the object, or the part of its longitudinal extent that has been coated/impregnated, enters a drying zone in which the coated/impregnated surface is irradiated with infrared radiation. The coating and/or impregnation agent can be applied all around the object or only to certain parts of its surface. Accordingly, the infrared radiation with radiant energy approximately uniformly distributed over the coated or impregnated surface is preferably incident simultaneously over the entire coated or impregnated surface of a longitudinal section of the object. Preferably a plurality of radiation sources are used for this purpose, and/or the radiation is appropriately diverted by scattering and/or

reflection.

So that the drying process can be stopped as soon as possible after application, a design is preferred in which the object, more specifically its longitudinal sections enter the drying zone immediately after leaving the application zone or even when they have only partially passed through the application zone. Apparatus is already known for applying liquid or pasty coatings and/or impregnation agents in which the agent is transported within the application zone by a stream of gas, which carries the agent from the reservoir where it is stored and deposits it on the surface of the object. For example, the coating systems in the "VACUMAT" series produced by the Schiele Maschinenbau GmbH, Kapellenstr. 7, D-56651 Niederzissen function according to this principle. In a further development of the invention, the gas stream is preferably used to cool one or more sources of infrared radiation before it reaches the reservoir, and/or to cool other components involved in irradiation within the drying zone, such as reflectors, radiation filters and/or partitions that are transparent to the radiation. In the case of coating agents and/or impregnation agents the viscosity of which is improved by warming, the heat acquired by the gas during the

cooling process is particularly advantageous. This heat, alone or in combination with additional heating, raises the temperature of the coating and/or impregnation agent as desired.

5 The means proposed for use as a drying means in accordance with the invention is an infrared lamp designed for drying an object coated or impregnated with a coating and/or impregnation agent. Preferably the infrared lamp is a halogen lamp.

10 In a further development the infrared lamp is constructed as a tubular radiator with an incandescent filament that extends linearly within a tube that is transparent to radiation, in particular a quartz-glass tube.

15 In another further development the infrared lamp is combined with a reflector element that extends along the tube and has a groove-like cross section, enclosing the tube at the back in such a way that the infrared radiation is intensified by the addition of reflected radiation to the radiation emitted towards
20 the front side.

 In the following the invention is explained in greater detail with reference to exemplary embodiments and to the attached drawing. However, the
25 invention is not restricted to these exemplary

embodiments. The individual figures in the drawing are as follows.

Fig. 1 shows a profiled piece coated on two sides, in which pigments are migrating to the interior before the drying has ended,

Fig. 2 shows a freshly lacquered wooden surface,

Fig. 3 shows the wooden surface according to Fig. 2 after the wood fibres have become raised,

Fig. 4 shows an apparatus for coating and drying objects.

Figure 1 shows a profiled piece 1 made of moderately dense fibrous material (MDF). The MDF profile 1 is freshly coated with a layer 2 of water-based lacquer. However, the lacquer layer 2 has already been on the MDF profile 1 long enough for the colouring pigments 6 that had been contained in the layer 2 to have migrated out. This migration is indicated by three arrows in the left half of the picture. The situation represented in Fig. 1 corresponds to a time ca. 3 seconds after the beginning of the application process in which the lacquer layer 2 is put onto the object.

In accordance with the invention the situation represented in Fig. 1 is prevented from occurring because the drying is completed in less than 3 seconds, in particular within one second after the beginning of the application process.

Figure 2 shows a coated surface of part of a wooden profile 5 in cross section. The coating consists of a layer 2 of water-based lacquer. The wooden profile 5 comprises fibres 4 that end at the surface of the profile 5. The surface was polished before coating and is correspondingly smooth.

Figure 3 shows the wooden profile 5 according to Fig. 2 at a later time. Because the drying of the water-based lacquer layer 2, or of the layer 2 and the profile 5, was not completed in time, since the object was in the state shown in Fig. 2 water has penetrated into the fibres 4 and into spaces 3 between the fibres 4, as a result of which the fibres 4 have become raised up and both the surface of the profile 5 that bears the lacquer layer and the outer surface of the layer 2 itself have become rough and uneven. The purchasers of industrially manufactured products, in particular, will not accept such a surface structure. Therefore a secondary treatment is required, usually smoothing of the dried outer surface of the lacquer followed by

application of another coat of lacquer.

In order to keep the wooden profile 5 permanently in the state shown in Fig. 2, which represents an arbitrary point in time less than 5 seconds after application of the layer 2 of water-based lacquer was begun, in accordance with the invention the drying is completed before the 5 seconds have elapsed, in particular within 1 second after the beginning of the application process.

Figure 4 shows a cross section of an apparatus for the lacquering of wooden piece goods. As represented in Fig. 4 the piece of wood is being conveyed from left to right, by means of conveyor mechanisms familiar to one skilled in the art. In this process high operating speeds, i.e. transport speeds, are desirable, in particular transport speeds of 8-80 m/min or even, when special feed aggregates are employed, transport speeds of up to 240 m/min. Such special aggregates are driven, for example, by two synchronously controlled motors and take up relatively little space.

The wooden piece goods are exemplified in Fig. 4 specifically by a wooden profile 5, a section of which was shown in Fig. 2. The profile is about 2 m long and is being transported at a velocity of 1 m/s,

or 60 m/min. Coming from the left, it first passes through an application chamber 20, the dimensions of which in the transport or longitudinal direction define an application zone. Immediately thereafter, i.e. at no spatial distance from the application chamber 20, is disposed the drying zone of the apparatus, which is defined by a longitudinal section of the transport path that can be exposed to infrared radiation. For this purpose the apparatus comprises two halogen lamps 11 that extend perpendicular to the plane of the drawing in Fig. 4. The halogen lamps 11 are constructed as tubular radiators. Each comprises a quartz-glass tube 13 and a tungsten wire 12 disposed approximately in the central line of the associated quartz-glass tube. The tungsten wire 12 serves as radiation emitter. During the period of irradiation an electrical current flows through the tungsten wire 12, so that it is at a temperature of about 3200 K.

The radiation emitted by the halogen lamps 11 either travels directly towards the piece of wood to be dried or reaches it indirectly. There may be several different indirect paths.

The halogen lamps 11 are combined with a lamp reflector element 10 comprising two groove-like recesses that extend along the quartz-glass tubes 13

and in cross section are partially occupied by the halogen lamps 11. The surface of the underside of the lamp reflector element 10, including the surface of the groove-like recesses, is such as to reflect infrared radiation. For example, the lamp reflector element 10 is made of aluminium and the reflecting surface of the lamp reflector element 10, called the upper reflector surface 14 of the apparatus, is formed by polishing the aluminium.

In order to ensure effective infrared irradiation, on the right-hand side of the drying zone a side reflector element 16 is disposed, the inner surface of which, facing the drying zone, is a lateral reflector surface 15 designed to reflect infrared radiation. A bottom reflector element 19 is also provided in the lower region of the drying zone, with lower 17 and lateral 15 reflector surfaces facing inwards towards the drying zone. Finally, the external surface of the part of the application chamber 20 that faces towards the drying zone is constructed as a lateral reflector surface 15. Because the apparatus is shown in section in Fig. 4, additional reflector surfaces above and below the plane of Fig. 4 are not visible; these complete the structure enclosing the drying zone, forming an almost completely closed space

around the drying zone within which the infrared radiation is approximately homogeneously distributed by reflections. Thus all sides of the wooden profile 5 are irradiated with approximately equal radiation flux density as the profile is transported through the drying zone.

Openings are disposed at several places in the wall around the drying zone: where the piece of wood enters the drying zone from the left, where it leaves on the right, and at the sides of the top, on the right and left of the lamp reflector element 10. These last openings serve to allow air to be blown along the lower surface of the lamp reflector element 10, in order to cool the halogen lamps 11 and the lamp reflector element 10. The cooling minimizes an undesired thermal radiation, which would be difficult to control, from the components of the apparatus other than the tungsten wires 12 that participate in the irradiation. These are in particular the quartz-glass tubes 13, the lamp reflector element 10, the side reflector element 16, the other side reflector elements (not visible in the figure), the bottom reflector element 19 and a glass partition 18 that subdivides the drying zone into a lower and an upper compartment. Cooling occurs separately in the upper and also in the

lower compartment.

Like the cooling in the upper compartment, that in the lower compartment is brought about by forced convection of air. The forced convection is driven by a pump (not shown) that sucks air in from the right, through the opening provided for the piece of wood to leave the drying zone, and draws the air into the lower compartment of the drying zone. There the air current first splits up so as to cool both the undersurface of the glass partition 18 and the reflector surfaces in the lower compartment. Then the air flows into the application chamber 20, through the opening on its right side, and there whirls up the liquid lacquer so as to form a homogenous mist of lacquer, which becomes deposited on the wooden profile 5. Next to the right-hand opening of the application chamber 20 the air flows closely along the coated surface of the wooden profile 5. Accordingly, the opening is dimensioned such that all the way around the wooden profile 5 there are only a few millimeters of clearance from the edge of the opening. At the left opening of the application chamber 20, through which the wooden profile 5 is conveyed into the application chamber 20, air also enters the application chamber 20. Here the space between the wooden profile 5 and the

edge of the opening is smaller, so as to ensure that most of the air entering the application chamber flows through the right-hand opening. Through an outlet 21 of the application chamber 20 the lacquer mist leaves the application chamber 20. By means of components of the apparatus not shown here the lacquer components of the lacquer mist are separated out, cleaned and returned to the reservoir of liquid lacquer 22 in the application chamber 20 by way of the inlet pipe 23.

Because the time taken for each individual longitudinal section of the wooden profile 5 to pass through the drying zone is about one second, and because drying has been completed when the profile leaves the drying zone, none of the colouring pigment migrates inward from the lacquered surface of the wooden profile 5, and the water and/or other solvents or dilution fluids contained in the liquid lacquer have no time to penetrate the wooden profile 5 sufficiently to cause its fibres to be raised up. To ensure complete drying, the halogen lamps 11 must emit sufficient radiation; therefore the radiation output is adjusted according to the area of surface to be dried per longitudinal section of the wood, in dependence on the transport speed. If the maximal radiation output does not suffice, additional halogen lamps (not shown) are

switched on.

The glass partition 18, which subdivides the drying zone, enables the flow of cooling air in the upper and the lower compartment to be independently matched to the local requirements. On the other hand, it uncouples the airstream needed for lacquering in the application chamber 20 from the temperature, and hence from the cooling requirements, of the halogen lamps 11 and the lamp reflector element 10. In alternative exemplary embodiments it can be desirable to heat the air that flows into the application chamber 20 through its right-hand opening to higher temperatures (for example, in order to warm the lacquer). In this case, alternatively or in addition a current of air flowing along the halogen lamps is directed into the application chamber.

List of Reference Numerals

1	MDF profile
2	Layer of water-based lacquer
3	Space between fibres
4	Fibre
5	Wooden profile
6	Colouring pigment
10	Lamp reflector element

- 11 Halogen lamp
- 12 Tungsten wire
- 13 Quartz-glass tube
- 14 Upper reflector surface
- 5 15 Lateral reflector surface
- 16 Side reflector elements
- 17 Lower reflector surface
- 18 Glass partition
- 19 Bottom reflector element
- 10 20 Application chamber
- 21 Outlet
- 22 Liquid lacquer
- 23 Inlet pipe for lacquer

CLAIMS

1. Method of drying coated and/or
impregnated objects (1; 5) that comprise a plurality of
regions, in particular fibres, that are each uniformly
structured, in particular for drying lacquered wood, in
cases such that a coating agent and/or impregnation
agent (22) applied to the surface of the object (1; 5)
contains a solvent and/or dilution fluid, in particular
water, that is to be driven out and/or bound during
drying, and such that the solvent or dilution fluid has
the property of penetrating into the object in the
undried state with the result that the uniformly
structured regions (4) change their position in the
object (1; 5) and, after a characteristic period of
time following application of the impregnation or
coating agent (22), alter the surface structure in such
a way as to make secondary treatment of the surface
necessary or desirable,
characterized in that the drying is completed before
the characteristic period of time has elapsed, by
irradiating the coated or impregnated surface with
infrared radiation.

2. Method of drying coated and/or
impregnated objects (1; 5), in particular lacquered
wood, in cases such that a coating agent and/or
impregnation agent (22) applied to the surface of the
5 object (1; 5) includes a component (6), in particular
colouring pigments, with the properties that

its presence in the region of the surface
and/or in the coating (2) ensures the quality of the
coating (2) or impregnation, however

10 in the undried condition it penetrates into
the object (1; 5) and after a characteristic period of
time following application of the impregnation or
coating agent (22) it is no longer present in
sufficient quantity in the region of the surface and/or
15 in the coating (2), so that a secondary treatment of
the surface, in particular a secondary lacquering, is
necessary or desirable,

characterized in that the drying is completed
before the characteristic period of time has elapsed,
20 by irradiating the coated or impregnated surface with
infrared radiation.

3. Method according to Claim 1 or 2,
characterized in that the infrared radiation comprises
substantial components, which bring about the drying,
in the near infrared, in particular at wavelengths
below 1.0 m.

4. Method according to Claim 3,
characterized in that the infrared radiation has a
spectral radiation flux density maximum in the near
infrared, in particular at a wavelength below 1.0 m.

5. Method according to Claim 4,
characterized in that the infrared radiation is emitted
as thermal radiation from a radiation emitter (12) that
is heated to temperatures of 2500 K or higher, in
particular 2900 K or higher.

6. Method according to one of the claims
1-5, characterized in that the drying is completed
within 5 seconds, in particular within 3 seconds, after
the application of the impregnation or coating agent.

7. Method according to one of the claims
1-6, characterized in that the object (1; 5) being
processed is conveyed continually in a longitudinal

direction, in the course of which it first passes through an application zone in which the coating and/or impregnation agent (22) is applied, and that the object (1; 5) or more specifically its coated or impregnated longitudinal sections are conveyed into a drying zone in which the coated or impregnated surface is irradiated with the infrared radiation.

8. Method according to Claim 7, characterized in that the object (1; 5) or more specifically its coated or impregnated longitudinal sections enter the drying zone immediately after leaving the application zone or after having partially passed through the application zone.

9. Method according to Claim 8, wherein the application of the impregnation or coating agent (22) in the application zone is brought about by a stream of gas that carries along the impregnation or coating agent (22), which is contained in a reservoir, and deposits it on the surface of the object (1; 5), characterized in that before the stream of gas reaches the reservoir, it is used to cool an infrared-radiation source (11) and/or to cool other components (16, 18, 19) involved in the irradiation in the drying zone,

such as reflectors, radiation filters and/or partitions transparent to radiation.

10. Employment of an infrared lamp (11) to dry an object (1; 5) coated or impregnated with a coating agent and/or impregnation agent (22), in particular to dry lacquered wood, in cases such that the nature of the coating agent and/or impregnation agent (22) is as described in Claim 1 and/or in Claim 2.

11. Employment according to Claim 10, wherein the infrared lamp (11) is a halogen lamp.

12. Employment according to Claim 10 or 11, wherein the infrared lamp (11) is constructed as a tubular radiator with an incandescent filament (12) that extends linearly within a tube (13) that is transparent to radiation, in particular within a quartz-glass tube.

13. Employment according to Claim 12, wherein the infrared lamp (11) is combined with a reflector element (10) that extends along the tube (13) and in cross section has a groove-like structure,

enclosing back side of the tube in such a way that the infrared radiation is intensified by addition of reflected radiation to the radiation emitted towards the front side.

5 14. Apparatus for coating and/or
impregnating objects, in particular wooden objects,
comprising

an application chamber (20) for continuously
applying an impregnation or coating agent,

10 a transport mechanism for continuously
transporting the objects from the application chamber
(20) to an irradiation device (10-19) for drying the
impregnation or coating agent,

15 wherein the transport mechanism is so
constructed that its speed is adjustable in such a way
that the object can be conveyed from the application
chamber (20) into the irradiation device (10-19) and
thereby dried within less than 5 seconds.

1/1




Fig. 1




Fig. 2




Fig. 3




Fig. 4

DECLARATION FOR PATENT APPLICATION AND POWER OF ATTORNEY

As a below named inventor, I hereby declare that my residence, post office address and citizenship are as stated below next to my name; I believe that I am the original, first and sole inventor (if only one name is listed below) or an original, first and joint inventor (if plural names are listed below) of the subject matter which is claimed and for which a patent is sought on the invention entitled "COATING OF OBJECTS," the specification of which (check one): ☐ is attached hereto; ☐ was filed on _____ as Application Serial No. _____ and was amended on _____ (if applicable); ☒ was filed as PCT International Application No. PCT/EP99/08003 on October 21, 1999 and was amended under Article 19 on _____ (if applicable). I hereby state that I have reviewed and understand the contents of the above-identified specification, including the claims, as amended by any amendment(s) referred to above. I acknowledge the duty to disclose to the Patent and Trademark Office all information known to me to be material to patentability as defined in 37 C.F.R. §1.56.

I hereby claim foreign priority benefits under 35 U.S.C. §119 of any foreign application(s) for patent or inventor's certificate or of any PCT international application(s) designating at least one country other than the United States of America listed below and have also identified below any foreign application(s) for patent or inventor's certificate or any PCT international application(s) designating at least one country other than the United States of America filed by me on the same subject matter having a filing date before that of the application(s) of which priority is claimed:

19857045.7 Germany 10 December 1998
(Application Serial Number) (Country) (Day/Month/Year Filed)

Priority Claimed
☒ Yes ☐ No

(Application Serial Number) (Country) (Day/Month/Year Filed)

☐ Yes ☐ No

I hereby claim the benefit under 35 U.S.C. §119(e) of any United States provisional application(s) listed below:

(Application Serial Number) (Day/Month/Year Filed)

(Application Serial Number) (Day/Month/Year Filed)

I hereby claim the benefit under 35 U.S.C. §120 of any United States application(s) or PCT international application(s) designating the United States of America listed below and, insofar as the subject matter of each of the claims of this application is not disclosed in the prior application(s) in the manner provided by the first paragraph of 35 U.S.C. §112, I acknowledge the duty to disclose to the Office all information known to me to be material to patentability as defined in 37 C.F.R. §1.56 which occurred between the filing date of the prior application(s) and the national or PCT international filing date of this application:

(Application Serial Number) (Day/Month/Year Filed) (Status-Patented, Pending or Abandoned)

(Application Serial Number) (Day/Month/Year Filed) (Status-Patented, Pending or Abandoned)

I hereby declare that all statements made herein of my own knowledge are true and that all statements made on information and belief are believed to be true; and further that these statements were made with the knowledge that willful false statements and the like so made are punishable by fine or imprisonment, or both, under 18 U.S.C. §1001 and that such willful false statements may jeopardize the validity of the application or any patent issued thereon.

This application and transmit all business in the Patent and Trademark Office requested thereon;

+49 89 21218670

S.12

John E. Langman (12,104)
John M. Gonsale (12,111)
Nancy P. Gonsale (12,122)
Edward M. O'Toole (12,177)
Michael P. Owen (12,147)
Teresa B. Jaffe (12,143)
Carl B. Moore, Jr. (12,157)
Richard K. Anderson (12,151)

Robert D. Ernst (12,177)
Robert A. Hoffmann (12,182)
James P. Zeller (12,191)
William E. McGowan (12,192)
Richard A. Schaefer (12,193)
Anthony Manno (12,195)
Christopher A. Gosholt (12,196)
Kevin D. Hogg (12,197)

Jeffrey S. Sharp (12,198)
James P. Hagg (12,199)
James L. Nagel (12,201)
Richard M. La Barge (12,204)
Lillian M. La Barge, M.D. (12,207)
Douglas C. Winkler (12,210)
Edward M. Gonsale (12,211)

Anthony G. Jaffe (12,212)
James A. Jaffe (12,213)
Roger A. McGowan (12,214)
David A. Goss (12,215)
Gregory C. Meyer (12,216)
Harold S. Walker (12,217)
WILLIAM E. Mortel (12,218)

Send correspondence to: NANCY P. GONSALE

FIRM NAME

Mathias O'Toole, Gonsale,
Murray & Davis

PHONE NO.

312-44-6390

FAX

6000 South Tower
250 South Wacker Drive

CITY & STATE

Chicago, Illinois

ZIP CODE

60604-6003

First Name of Firm or Sole Inventor	Mathias O'Toole
Address Address - Street	Post Office Address - Street
Branch/Office Straße 27	Branch/Office Straße 27
City (Zip)	City (Zip)
Branch/Office 60603	Branch/Office 60603
State or Country	State or Country
Federal Republic of Germany	Federal Republic of Germany
Date	Signature
8	8

First Name of Inventor, if any	Christian
RAINER GAUS	Christian
Address Address - Street	Post Office Address - Street
Branch/Office Straße 27	Branch/Office Straße 27
City (Zip)	City (Zip)
Branch/Office 60603	Branch/Office 60603
State or Country	State or Country
Federal Republic of Germany	Federal Republic of Germany
Date	Signature
8	8

First Name of Inventor, if any	Christian
MARTIN SCHULMEYER	Christian
Address Address - Street	Post Office Address - Street
Branch/Office 11	Branch/Office 11
City (Zip)	City (Zip)
Branch 65540	Branch 65540
State or Country	State or Country
Federal Republic of Germany	Federal Republic of Germany
Date	Signature
8	8

First Name of Inventor, if any	Christian
STEFAN SCHIELE	Christian
Address Address - Street	Post Office Address - Street
Branch/Office 153	Branch/Office 153
City (Zip)	City (Zip)
Branch 56601	Branch 56601
State or Country	State or Country
Federal Republic of Germany	Federal Republic of Germany
Date	Signature
8	8

GESAMT SEITEN 12

01/09/2001 18:02

+49-9333-07104

000001355110

BILD.STATTE LÖNGFURT

S.

06/06

01 AUG 2001 10:21

ADPH08 AG

08081395110

P.6

30-JUL-2001 13:36

MEISSNER, BOLTE & PARTNER

+49 89 2128670

S.12

this application and instruct all business in the Patent and Trademark Office connected therewith;

John G. Longmire (16,500)
 Allan G. Garwood (22,200)
 Hans P. Schaefer (22,300)
 Robert M. O'Toole (22,477)
 Michael P. Byrne (23,000)
 Trevor B. Smith (23,000)
 Carl E. Moore, Jr. (23,487)
 Richard G. Anderson (24,220)

Patrick D. Engel (26,877)
 Richard B. Hoffmann (26,910)
 James P. Zeller (28,491)
 William A. Macintosh (28,740)
 Richard A. Johnson (30,280)
 Anthony Marino (30,500)
 Christine A. Doherty (31,200)
 Kevin D. Hogg (31,250)

Jeffrey S. Sharp (31,379)
 Martin A. Hirsch (32,277)
 James J. Napoli (32,300)
 Richard M. La Barge (32,354)
 Louis M. Hirsch (32,549)
 Douglas C. Bradburne (32,710)
 Robert M. Gormley (34,820)

Anthony G. Sider (34,278)
 James A. Pugh (37,611)
 Roger A. Magermann (37,641)
 David A. Galt (38,123)
 Gregory C. Meyer (38,220)
 Michael R. Weller (38,379)
 William H. Martens (40,120)

Send correspondence to: Nate F. Scarfelli

FIELD NAME	FIELD NO.	STREET	CITY & STATE	ZIP CODE
Marshall, O'Toole, Garwood, Murray & Scarfelli	312-414-6300	6800 S. Loop 200 South Western Drive	Chicago, Illinois	60605-6002

Full Name of Firm or Sole Inventor	Citizenship
KAIKO BAR	Germany
Residence Address - Street	Post Office Address - Street
Bruckmühlstraße 27	Bruckmühlstraße 27
City (Zip)	City (Zip)
Bruckmühl 43052	Bruckmühl 43052
State or Country	State or Country
Federal Republic of Germany	Federal Republic of Germany
Signature	Signature

Full Name of Firm or Sole Inventor, if any	Citizenship
RAINER GAUS	Germany
Residence Address - Street	Post Office Address - Street
Bruckmühlstraße 27	Bruckmühlstraße 27
City (Zip)	City (Zip)
Bruckmühl 43052	Bruckmühl 43052
State or Country	State or Country
Federal Republic of Germany	Federal Republic of Germany
Signature	Signature

Full Name of Firm or Sole Inventor, if any	Citizenship
MARTIN SEDLMEYER	Germany
Residence Address - Street	Post Office Address - Street
Sandstrasse 11	Sandstrasse 11
City (Zip)	City (Zip)
Munich 85340	Munich 85340
State or Country	State or Country
Federal Republic of Germany	Federal Republic of Germany
Signature	Signature

Full Name of Firm or Sole Inventor, if any	Citizenship
STEFAN SCHIEL	Germany
Residence Address - Street	Post Office Address - Street
Bruckmühlstraße 133	Bruckmühlstraße 133
City (Zip)	City (Zip)
Munich 85340	Munich 85340
State or Country	State or Country
Federal Republic of Germany	Federal Republic of Germany
Signature	Signature

Fax No.	089-2128670
Att. to	Valentin
Von:	9.10.2001
Datum:	7.10.01
Seiten:	1

MEISSNER, BOLTE & PARTNER		Po	Sk
EING 07. AUG. 2001		Sj	Sk
		Bo	Sk
		Kr	Sk
WV		Za	cp
LT		Tx	Bu
		Hr	Sk

Received Time Sep. 6. 12:13PM

Print Time 7 Sep. 6. 12:17PM